



Polyester sprayable primers for plug finition and preparation of metallic parts before painting

Reference	Application	Viscosity/poises	Thixotropic index	Gel time / min (On 200gr mass at 20°C, 1% MEKP 50)	Sandable after / Mn.	Density (± 0,05)	Comments
AC-1205	Gravity gun / Machine	70-80	≥ 4	20-30	60	1,1	Easy to sand, low level of dirt on sanding paper, good surface finish, no porosity. Enables easy defect correction. Low styrene emission
AC-1900	Machine	70-80	≥ 4	2-4	30-45	1,1	High reactivity. Dry when touching in 5 minutes. Very good surface tension. Enables lower thickness. Easy to sand, low dirt level on sanding paper. Very good adhesion on all kind of metals. Corrosion resistant. Low styrene emission

For more information please refer to Products and Applications pages : [EuromereSprayCore.com](http://EuromereSprayCore.com)



Pour télécharger ce pdf : Fichier > Enregistrer sous

Download this pdf : File > Save as